

Amendments to the Claims

1. (Currently Amended) A tire having a tread comprised of a vulcanizable rubber composition comprising:
 - (A) 100 parts by weight of at least one diene-based elastomer wherein selected from the group consisting of natural or synthetic cis 1,4-polyisoprene rubber, 3,4-polyisoprene rubber, styrene/butadiene copolymer rubbers, isoprene/butadiene copolymer rubbers, styrene/isoprene copolymer rubbers, styrene/isoprene/butadiene terpolymer rubbers, cis 1,4-polybutadiene rubber and medium to high vinyl polybutadiene rubber having a vinyl 1,2- content in a range of about 15 to about 85 percent and emulsion polymerization prepared butadiene/acrylonitrile copolymers;
 - (B) from about 1 to about 60 phr of a starch/synthetic plasticizer composite; and
 - (C) from ~~1.5 to 8~~ 4.5 to 10 phr of an adduct of maleic anhydride and polybutadiene.
2. (Previously Presented) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene has a number average molecular weight of from about 1,500 to about 10,000.
3. (Previously Presented) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene has a number average molecular weight of from about 2,500 to about 7,500.
4. (Previously Presented) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene has an average of from about 2 to about 20 functional groups based on maleic anhydride per polymer chain.
5. (Previously Presented) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene has an average of from about 3 to about 12 functional groups based on maleic anhydride per polymer chain.
6. (Canceled)
7. (Previously Presented) The tire of claim 1, wherein said starch/synthetic plasticizer

composite comprises starch composed of amylose units and amylopectin units in a ratio of about 15/85 to about 35/65, and has a softening point according to ASTM No. D1228 in a range of about 180°C to about 220°C, provided that said starch/plasticizer composite has a softening point in a range of about 110 to about 160°C according to ASTM No. D1228.

8. (Previously Presented) The tire of claim 1, wherein said starch/synthetic plasticizer composite comprises a plasticizer that is a liquid at 23°C and is selected from at least one of poly(ethylenevinyl alcohol), cellulose acetate and plasticizers based, at least in part, upon diesters of dibasic organic acids and forms said starch/plasticizer composite having a softening point in a range of about 110 to about 160°C when combined with said starch in a weight ratio in a range of about 1/1 to about 3/1.

9. (Previously Presented) The tire of claim 1 wherein said starch/synthetic plasticizer composite comprises a plasticizer having a softening point of less than the said starch and less than 160°C and is selected from at least one of poly(ethylenevinyl alcohol), cellulose acetate and copolymers, and hydrolyzed copolymers, of ethylene-vinyl acetate copolymers having a vinyl acetate molar content of from about 5 to about 90, alternatively about 20 to about 70, percent, ethylene-glycidyl acrylate copolymers and ethylene-maleic anhydride copolymers.

10. (Previously Presented) The tire of claim 1, wherein said at least one diene elastomer is selected from the group consisting of homopolymers of isoprene and 1,3-butadiene and copolymers of isoprene and/or 1,3-butadiene with a aromatic vinyl compound selected from at least one of styrene and alphanemethylstyrene.

11. (Previously Presented) The tire of claim 1, further comprising from about 20 to about 85 phr of carbon black.

12. (Previously Presented) The tire of claim 1, further comprising from about 10 to

about 85 phr of silica.

13. (Cancelled)
14. (Cancelled)
15. (Cancelled)
16. (Previously Presented) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene has a glass transition temperature in a range of from about -70°C to about 0°C.
17. (Currently Amended) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene is present in a concentration ranging from ~~4.5 to 6~~ 6 to 10 phr.
18. (Canceled)
19. (Canceled)
20. (Newly Added) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene is present in a concentration ranging from 7.5 to 10 phr.
21. (Newly Added) The tire of claim 1, wherein said adduct of maleic anhydride and polybutadiene is present in a concentration ranging from 9 to 10 phr.